

Silicon Carbide for metallurgical applications is used in steel foundries as an inoculant or deoxidizing agent, and as an alloying element, replacing the carbon / ferrosilicon additions in induction and cupola furnaces.

**Packaging** 25 kg paper bags or loose material. 1.000 kg – 1.500 kg big bags.

## SIKA® MET 90%

	SiC	Si	C
<b>Typical Chemistry</b>	~ 90.00 %	~ 63 %	~ 27 %
<b>Standard fractions</b>	0 - 10mm / 1 - 10mm / 10 - 50mm		

## SIKA® MET 85%

	SiC	Si	C
<b>Typical Chemistry</b>	~ 85.00 %	~ 59.5 %	~ 25.5 %
<b>Standard fractions</b>	0 - 10mm / 1 - 10mm / 10 - 50mm		

## SIKA® MET 80%

	SiC	Si	C
<b>Typical Chemistry</b>	~ 80.00 %	~ 56 %	~ 24 %
<b>Standard fractions</b>	0 - 10mm / 1 - 10mm / 10 - 50mm		

## SIKA® MET 70%

	SiC	Si	C
<b>Typical Chemistry</b>	~ 70.00 %	~ 49 %	~ 21 %
<b>Standard fractions</b>	Briquettes		

The information contained in this Product Information Document is the sole property of Saint-Gobain, and cannot be distributed outside Saint-Gobain or its Customers, entirely or by parts, without the prior consent of Saint-Gobain. The Product Information Documents display typical characteristics for Saint-Gobain's products as currently produced in Saint-Gobain's various manufacturing locations. These typical characteristics do not constitute a precise Customer Specification, which has to be elaborated separately between the Customer and Saint-Gobain in the frame of a commercial offer. Only with this precise Customer Specification can Saint-Gobain be bound to any commitment or liability regarding the quality of its products.