

Green Silicon Carbide grains to be used as a loose abrasive in wire sawing applications.

Green silicon carbide produced in accordance with existing industrial standards or according to individual customer specifications.

Saint-Gobain OPTICUT is used to slice wafers out of silicon ingots or other hard brittle materials, and is designed to optimize cut rate while minimizing TTV and subsurface damage.

Packaging 1.000 kg big bags

Typical Chemistry


SiC	Free-C	Free-SiO ₂	Free-Si	Fe ₂ O ₃
99.50 %	0.10 %	0.20 %	0.10 %	0.10 % max

Grit Sizes and Shapes

FEPA Standard		
Grit No.	ds 50% μm	% mean circularity (ds 3% - ds 50%)
F600	8.3 - 10.3	< 0.90
F800	5.5 - 7.5	< 0.90
F1000	4.1 - 5.3	n.a.

Analytical Procedures:

Particle Size Distribution is measured according to FEPA Standard 42-2:2006
 Chemistry according ANSI B74.15-1992 (R2000)
 Circularity measured by Malvern Sysmex FPIA-3000



SiC particles characterized by intermediate angular shapes, providing good balance between cut rate and surface finish.

The information contained in this Product Information Document is the sole property of Saint-Gobain, and cannot be distributed outside Saint-Gobain or its Customers, entirely or by parts, without the prior consent of Saint-Gobain. The Product Information Documents display typical characteristics for Saint-Gobain's products as currently produced in Saint-Gobain's various manufacturing locations. These typical characteristics do not constitute a precise Customer Specification, which has to be elaborated separately between the Customer and Saint-Gobain in the frame of a commercial offer. Only with this precise Customer Specification can Saint-Gobain be bound to any commitment or liability regarding the quality of its products.